

55210: BASE 55219: CURING AGENT 95370

| | |
|--------------------------------|--|
| Description: | HEMPATHANE TOPCOAT 55210 is a two-component, glossy acrylic polyurethane coating, cured with aliphatic isocyanate, with good gloss and colour retention. |
| Recommended use: | As a finishing coat for protection of structural steel in severely corrosive atmospheric environment, where light-fastness and gloss retention are required. Minimum temperature for curing is -10°C/14°F. |
| Service temperature: | Maximum, dry exposure only: 120°C/248°F see REMARKS overleaf |
| Certificates/Approvals: | Complies with European Fire Standard EN 13501-1; classification B-s1, d0. Approved as a low flame spread material when used as part of a predefined paint system. Please refer to "Declaration of Conformity" on www.Hempel.com for further details. Complies with EU Directive 2004/42/EC: subcategory j. |
| Availability: | Part of Group Assortment. Local availability subject to confirmation. |

PHYSICAL CONSTANTS:

| | |
|-----------------------------|---|
| Shade nos/Colours: | 10000*/ White. |
| Finish: | Glossy |
| Volume solids, %: | 51 ± 1 |
| Theoretical spreading rate: | 10.2 m ² /l [409 sq.ft./US gallon] - 50 micron/2 mils |
| Flash point: | 33 °C [91.4 °F] |
| Specific gravity: | 1.2 kg/litre [10.1 lbs/US gallon] |
| Surface-dry: | 1 hour 20°C/68°F |
| Through-dry: | 8 hour(s) 20°C/68°F |
| Fully cured: | 7 day(s) 20°C/68°F |
| VOC content: | 442 g/l [3.7 lbs/US gallon] |
| Shelf life: | 3 years for BASE and 2 years (25°C/77°F) for CURING AGENT from time of production. <i>*Wide range of colours available via Hempel's MULTI-TINT system.</i> |

The physical constants stated are nominal data according to the HEMPEL Group's approved formulas.

APPLICATION DETAILS:

| | |
|--------------------------------|---|
| Version, mixed product: | 55210 |
| Mixing ratio: | BASE 55219: CURING AGENT 95370 7:1 by volume |
| Application method: | Airless spray / Brush |
| Thinner (max.vol.): | see REMARKS overleaf / 08080 (5%) |
| Pot life: | 4 hour(s) 20°C/68°F |
| Nozzle orifice: | 0.017 - 0.019 " |
| Nozzle pressure: | 150 bar [2175 psi] (Airless spray data are indicative and subject to adjustment) |
| Cleaning of tools: | HEMPEL'S THINNER 08080 or 08510 |
| Indicated film thickness, dry: | 50 micron [2 mils] see REMARKS overleaf |
| Indicated film thickness, wet: | 100 micron [4 mils] |
| Overcoat interval, min: | see REMARKS overleaf |
| Overcoat interval, max: | see REMARKS overleaf |

| | |
|----------------|--|
| Safety: | Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult HEMPEL Safety Data Sheets and follow all local or national safety regulations. |
|----------------|--|

SURFACE PREPARATION: According to specification.

APPLICATION CONDITIONS: Apply only on a dry and clean surface with a temperature above the dew point to avoid condensation. Minimum temperature for curing is: -10°C/14°F. At the freezing point and below be aware of the risk of ice on the surface, which will hinder adhesion. The film formation may be adversely affected by light rain, high humidity and/or condensation during application and the following interval after application: 10 hours , 20°C/68°F
In confined spaces provide adequate ventilation during application and drying.

PRECEDING COAT: According to specification. Recommended systems are: HEMPADUR45141/45143, HEMPADUR MASTIC 45880/45881

SUBSEQUENT COAT: None.

REMARKS:

VOC - EU Directive 2004/42/EC:

| Product | As supplied | 10 vol. % thinning | Limit phase II, 2010 |
|------------|-------------|--------------------|----------------------|
| 5521010000 | 442 g/l | 483 g/l | 500 g/l |

For VOC of other shades, please refer to Safety Data Sheet.

Colours/Colour stability:

Colour stability for some shades may be effected by exposure to harsh chemical atmospheres. This does not affect the performance of the coating.
For certain colours extra coats may be necessary to obtain full opacity.

For aluminium pigmented shades scratching actions or high humidity/water may cause discolouration/ disturbances of the surface. This will have no influence on the performance. This phenomenon may be avoided by applying a clear varnish.

Weathering/service temperatures:

At service temperature above 100°C/212°F, slight discolouration may be expected.

Film thicknesses/thinning:

The type and amount of thinner depend on application conditions, application method, temperature, ventilation, and substrate. THINNER 08080 is recommended in general.
Airless spray: 5-10% thinning is recommended. Under extreme conditions up to more than 20% may be necessary to obtain satisfactory film formation.

Electrostatic spray: 10% thinning is recommended. Contact HEMPEL for more information.
May be specified in another film thickness than indicated depending on purpose and area of use. This will alter spreading rate and may influence drying time and overcoating interval. Normal range dry is: 40-75 micron/1.6-3 mils.

Shades:

This product is available in several aluminium pigmented shades with different volume solids content. Contact HEMPEL for more information.

Curing agent:

CURING AGENT 95370: is sensitive to moisture.
Even small traces of water in the mixed paint will reduce the pot life and result in film defects.
Open curing agent cans with caution as overpressure might exist. Store in a dry place and keep the can tightly closed until use.

Overcoating:

Overcoating intervals related to later conditions of exposure: If the maximum overcoating interval is exceeded, roughening of the surface is necessary to ensure intercoat adhesion.
Before overcoating after exposure in contaminated environment, clean the surface thoroughly with high pressure fresh water hosing and allow drying.

A specification supersedes any guideline overcoat intervals indicated in the table.

| Environment | Atmospheric, medium | | | | | |
|-------------|---------------------|------|------------|------|-------------|------|
| | -10°C (14°F) | | 0°C (32°F) | | 20°C (68°F) | |
| | Min | Max | Min | Max | Min | Max |
| HEMPATHANE | 30 h | None | 18 h | None | 6 h | None |

NR = Not Recommended, Ext. = Extended, m = minute(s), h = hour(s), d = day(s)

Note:

HEMPATHANE TOPCOAT 55210 For professional use only.

ISSUED BY:

HEMPEL A/S

5521010000

This Product Data Sheet supersedes those previously issued.

For explanations, definitions and scope, see "Explanatory Notes" available on www.hempel.com. Data, specifications, directions and recommendations given in this data sheet represent only test results or experience obtained under controlled or specially defined circumstances. Their accuracy, completeness or appropriateness under the actual conditions of any intended use of the Products herein must be determined exclusively by the Buyer and/or User.
The Products are supplied and all technical assistance is given subject to HEMPEL's GENERAL CONDITIONS OF SALES, DELIVERY AND SERVICE, unless otherwise expressly agreed in writing. The Manufacturer and Seller disclaim, and Buyer and/or User waive all claims involving, any liability, including but not limited to negligence, except as expressed in said GENERAL CONDITIONS for all results, injury or direct or consequential losses or damages arising from the use of the Products as recommended above, on the overleaf or otherwise. Product data are subject to change without notice and become void five years from the date of issue.